



Data sheet Psi values for facade profiles

based on determination of the equivalent thermal conductivity of spacers by measurement

ROLLTECH

ROLLTECH A/S - an Alu-Pro Group Company

ALU-PRO

ROLLTECH A/S, Johs. E. Rasmussens Vej 12, DK-9800 Hjørring Alu-Pro S.r.l., Via A. Einstein 8, Z.I., IT - 30033 Noale

Profile description	Product name	Spacer height in mm	Material	Thickness d in mm
	CHROMATECH ultra F1	6.9	Stainless steel	0.1
		Spacer category B	PVC	0.9

Representative glass constructions	Wood/metal	Metal with thermal break (d ₁ = 100 mm)	Metal with thermal break (d ₁ = 200 mm)
Representative facade profiles			
Representative psi value double-sheet thermally insulating glass W/mK 	0.066	0.089	0.094
Representative psi value triple-sheet thermally insulating glass W/mK 	0.061	0.076	0.079
Two Box model Characteristic values 	Space between panes in mm	$\lambda_{eq,2B}$ in W/mK	
	Can be used for all spacer widths	Box 1 · h ₁ = 6 mm 0.40	Box 2 · h ₂ = 6.9 mm 0.28

Explanations

The equivalent thermal conductivity has been determined in accordance with ift guideline WA-17engl/1 "Thermally improved spacers – Determination of the equivalent thermal conductivity by measurement". The representative linear heat transfer coefficients (representative psi values) determined thereby apply to typical facade profiles and glazing for determination of the coefficients of thermal conductivity U_{CW} of curtain walls. They have been determined under the framework conditions (frame profiles, glazing, glass mounting depth, back covering, primary and secondary sealant) defined in ift guideline WA-22engl/1 "Thermally improved spacers – Part 3: Determination of the representative psi value for facade profiles". This guideline also governs the area of validity and application of the representative psi values. In order to avoid rounding errors, the psi values in the data sheet have been specified to the nearest 0.001 W/mK. The calculation method for determining the psi values has an accuracy of ± 0.003 W/mK. Differences of less than 0.005 W/mK are not significant. Further information can be found in the bulletin 004/2008 "Guide to Warm Edge" published by Bundesverband Flachglas.

Characteristic values determined by:

